

Tableau de résistance chimique des PTFE Chargé

	Charges		
	CarbonE/Graphite	verre	Bronze
Acetaldehyde	A	A	A
Acetone	A	A	A
Aluminum Sulphate	A	A	B
Ammonium chloride	A	A	C
Ammonium hydroxide	A	B	C
Aniline	A	A	C
Benzene	A	A	A
Brine	A	A	A
Bromine (anhydrous)	C	B	C
Carbon Disulphide	A	A	A
Chloroacetic acid	A	A	B
Chlorobenzene	A	A	A
Chloroform	A	A	A
Chromic acid	B	B	C
Citric acid	A	A	A
Diethyl ether	A	A	A
Ethylene glycol	A	A	A
Fatty acids	A	A	A
Ferric Chloride	A	A	C
Ferric sulphate	A	A	C
Fluorosilicic acid	B	C	C
Formic acid	A	A	A
Freon (liquid)	A	A	A
Hydro boric acid	A	B	C
Hydrochloric acid	A	B	C
Hydrocyanic acid	A	B	C
Hydrogen sulphide (solution)	A	C	C
Lead acetate	A	A	C
Maleic acid	A	A	B
Mercury salts	A	A	C
Molasses	A	A	B
Naphtha	A	A	B
Naphthalene	A	A	B
Nickel salts	A	A	A
Nitric acid	C	B	C
Nitro benzene	A	A	A
Phenol	A	B	A
Phosphoric acid	A	A	C

	Charges		
	CarbonE/Graphite	verre	Bronze
Picric acid	A	A	A
Pyridine	A	A	C
Salicylic acid	A	A	B
Silver nitrate	A	A	C
Sodium carbonate	A	A	A
Sodium hydroxide	A	B	A
Sodium nitrite	A	A	A
Sodium peroxide	B	A	C
Sodium silicate	A	C	A
Sodium sulphide	A	A	C
Starch	A	A	A
Sulphuric acid	B	A	C
Tallow	A	A	A
Tannic acid	A	A	A
Tartaric acid	A	A	A
Trichloroethylene	A	A	B
Zinc chloride	A	A	C

A = Très bonne résistance

B = moyenne résistance

C = Non recommandé